

KOSTIC Acrylic Adhesive Film Line Up

※ Peel strength indicates a measured at a peeling angle of 180 degrees, a peeling speed of 300mm/min.

(Rev.2 2015.10.27)

K	A	P	-	IM	50	50	B	→	① KOSTIC	② A: Acrylic E: Electrification	③ PSA film	④ PSA Type
①	②	③	④	⑤	⑥	⑦			⑤ Base Film Thickness	⑥ Liner Film Thickness, W : White PET	⑦ 개발 순서	

Series	Grade	Film Type	Adhesive Type	Peel Strength (gf/25mm)	Thickness(μm)		Antistatic (Ω/□)	Applications
					Base Film	Total		
KAP-BK	KAP-BK5050A	PET	Acrylic	3.0 ± 2.0	50	70	-	Glass 보호용, 공정 보호용
KAP-CX	KAP-CX5050F	PET	Acrylic	5.0 ± 2.0	50	65	-	메탈메쉬 보호용, 공정 보호용
	KAP-CX7550D	PET	Acrylic	5.0 ± 2.0	75	95	-	Glass 보호용, 공정 보호용
	KAP-CXB5050A	Blue PET	Acrylic	5.0 ± 2.0	50	70	-	카메라 홀 보호용
KAP-IM	KAP-IM5050A = KPP-210A	PET	Acrylic	10.0 ± 3.0	50	70	-	Glass 보호용, 공정 보호용
	KAP-IM5050B	PET	Acrylic	10.0 ± 3.0	50	65	-	ITO Film 보호용, Glass 보호용
	KAP-IM7550C	PET	Acrylic	10.0 ± 3.0	75	90	-	Glass 보호용, 공정 보호용
	KAP-IM50W75A	PET	Acrylic	10.0 ± 3.0	50	70	-	Glass 보호용, 공정 보호용
	KAP-IM7525B	PET	Acrylic	10.0 ± 3.0	75	90	-	Glass 보호용, 공정 보호용
KEP-CS	KEP-CS25W50A	PET	Acrylic	7.0 ± 3.0	25	75	< 10 ¹¹	대전 방지용, Glass 보호용
KEP-HA	KEP-HA5025	PET	Acrylic	10.0 ± 3.0	50	73	< 10 ¹¹	대전 방지용, 공정 보호용

* Warranty :

All statements, technical information and recommendations about KOSTIC products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. We all KOSTIC products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

www.kostic.co.kr

Sales Team Tel : +81-31-984-2100, Sales Team FAX : +81-31-982-0458

R&D Team Tel : +81-31-949-0356, R&D Team Fax : +81-31-949-0549

KOSTIC KOREA CO., LTD