



Release Paper Line Up

* Release Force: TESA7475, 23°C x 20hrs 전처리(70g/㎠가압)
→ 4hrs 안정화, 180°Peel

PE/실리콘(S)	원지(PAPER)	두께(μm) Thickness	평량(g/㎡)	이형 범위(gf/25mm) Release Force	특이사항
단면PE/단면S	BG65(Blue Glassine)	70-80	75-85	경박(7-15)	*
	WG65(White Glassine)	70-80	75-85	경박(7-15)	*
	RY2000(황색박리지 95g)	130-140	110-120	경박(5-15), 중박(20-100)	초중박(200-300)가능
	RY3000(황색박리지 120g)	150-170	135-155	경박(5-15)/중박(20-100)	초중박(200-300)가능
	RB2000(옥색박리지/Blue 95g)	130-140	110-120	경박(5-15)/중박(20-100)	*
	CP70(White)	105-115	85-95	경박(5-15)	*
	WF90(양면용 모조지)	115-125	120-125	경박(5-15)/중박(20-100)	양면유광, 엠보이형지 포함
	WF120(양면용 모조지)	155-165	140-150	경박(5-15)	*
WF150(양면용 모조지)	175-190	160-170	경박(5-15)/중박(20-100)	*	

* 관리 및 주의사항:작업 전 실리콘 처리면 확인, 운반/적재 시 주의(사용 잔여분 포장주의), 정전기, 먼지 주의, 작업 정체 시 이형물성 변화 확인
* 친환경/환경규제 대응: RoHS 및 할로젠프리 만족, 기타 규제 경우 분석 및 비사용보증서 대응(DoC)

* Warranty :
All statements, technical information and recommendations about KOSTIC products are based upon tests believed to be reliable but do not constitute a guarantee or warranty.
We all KOSTIC products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

www.kostic.co.kr
 Sales Team Tel : +81-31-984-2100, Sales Team FAX : +81-31-982-0458
 R&D Team Tel : +81-31-949-0356, R&D Team Fax : +81-31-949-0549
KOSTIC KOREA CO., LTD