

KOSTIC Release Film Line Up

※ Release Force: TESA7475, 23°C x 20hrs 전처리(70g/㎡가압) → 4hrs 안정화, 180°Peel

(Rev.3 2015.10.27)

K	B	S	-	1	4	0S
①	②	③	④	⑤	⑥	

① KOSTIC	② BLU, MLCC, DAF	③ Silicone Release Film	④ 1: 단면코팅, 2: 양면코팅, 3: White PET
⑤ 1: 19μm, 2: 25μm, 3: 38μm, 4: 50μm, 5: 75μm, 6: 100μm, 7: 125μm	⑥ Silicone Type, AS: Antistatic, B: Blue PET		

Series	Release Type	Grade	Film Thickness (μm)	Release Force (gf/25mm)	Residual Ratio of Adhesive (%)	Antistatic (Ω/□)	Applications
KBS	초경박리	KBS-120S	PET 25	5.0 ± 2.0	≥ 80	-	고속타발용, Die Cutting용, Carrier용
		KBS-130S	PET 38	5.0 ± 2.0	≥ 80	-	전사코팅용, Die Cutting용, Carrier용
		KBS-140S	PET 50	5.0 ± 2.0	≥ 80	-	고속타발용, Die Cutting용, Carrier용
		KBS-150S	PET 75	5.0 ± 2.0	≥ 80	-	고속타발용, Die Cutting용, Carrier용
		KBS-160S	PET 100	5.0 ± 2.0	≥ 80	-	마스크팩용, Die Cutting용, Carrier용
		KBS-140SB	Blue PET 50	5.0 ± 2.0	≥ 80	-	Die Cutting용, Carrier용, 후 가공용
		KBS-150SB	Blue PET 75	5.0 ± 2.0	≥ 80	-	Die Cutting용, Carrier용, 후 가공용
		KBS-131S	PET 38	5.0 ± 2.0	≥ 80	-	Die Cutting용, Carrier용, 후 가공용
		KBS-141S	PET 50	5.0 ± 2.0	≥ 80	-	파스용, Die Cutting용, Carrier용
	경박리	KBS-140U	PET 50	8.0 ± 3.0	97 ± 3	-	OCA용, 후 가공용
		KBS-150U	PET 75	8.0 ± 3.0	97 ± 3	-	OCA용
		KBS-160U	PET 100	8.0 ± 3.0	97 ± 3	-	Die Cutting용, Carrier용, 후 가공용
		KBS-160T	PET 100	10.0 ± 3.0	97 ± 3	-	Die Cutting용, Carrier용, 후 가공용
		KBS-151B	PET 75	10.0 ± 3.0	97 ± 3	-	OCA용
		KBS-125B	PET 25	12.0 ± 3.0	97 ± 3	-	Die Cutting용, Carrier용, 후 가공용
		KBS-145B	PET 50	12.0 ± 3.0	97 ± 3	-	OCA용, 범용 합지용
		KBS-145BAS	PET 50	12.0 ± 3.0	97 ± 3	< 10 ⁹	Die Cutting용, Carrier용, 후 가공용
		KBS-155B	PET 75	12.0 ± 3.0	97 ± 3	-	Die Cutting용, Carrier용, 후 가공용
		KBS-165B	PET 100	12.0 ± 3.0	97 ± 3	-	Die Cutting용, Carrier용, 후 가공용
		KBS-355B	White PET 75	12.0 ± 3.0	97 ± 3	-	Die Cutting용, Carrier용, 후 가공용
		KBS-365B	White PET 100	12.0 ± 3.0	97 ± 3	-	Die Cutting용, Carrier용, 후 가공용
		KBS-140A	PET 50	15.0 ± 5.0	97 ± 3	-	OCA용, Die Cutting용, Carrier용
	중박리	KBS-140L	PET 50	20.0 ± 5.0	97 ± 3	-	Die Cutting용, Carrier용, 후 가공용
		KBS-151M	PET 75	23.0 ± 5.0	97 ± 3	-	OCA용
		KBS-150M	PET 75	25.0 ± 5.0	97 ± 3	-	OCA용
		KBS-140C	PET 50	35.0 ± 10.0	≥ 90	-	Die Cutting용, Carrier용, 후 가공용
		KBS-160C	PET 100	35.0 ± 10.0	≥ 90	-	Die Cutting용, Carrier용, 후 가공용
		KBS-140D	PET 50	45.0 ± 10.0	97 ± 3	-	OCA용, Die Cutting용, Carrier용
	중중박리	KBS-140K	PET 50	70.0 ± 20.0	≥ 90	-	Die Cutting용, Carrier용, 후 가공용
		KBS-140E	PET 50	80.0 ± 20.0	≥ 90	-	Die Cutting용, Carrier용, 후 가공용
		KBS-150E	PET 75	80.0 ± 20.0	≥ 90	-	Die Cutting용, Carrier용, 후 가공용
		KBS-150G	PET 75	130.0 ± 30.0	≥ 90	-	합지용, 후 가공용
		KBS-160G	PET 100	130.0 ± 30.0	≥ 90	-	Die Cutting용, Carrier용, 후 가공용
양면코팅	KBS-245BC	PET 50	12.0 ± 3.0	≥ 90	-	양면 Tape용, 후 가공용	
			35.0 ± 10.0	≥ 90	-		
양면코팅	KBS-255BL	PET 75	12.0 ± 3.0	≥ 90	-	양면 Tape용, 후 가공용	
			20.0 ± 5.0	≥ 90	-		
KCS	중박리	KCS-130B	PET 38	20.0 ± 5.0	≥ 90	-	MLCC(적층세라믹콘덴서) 공정용
	중중박리	KCS-340H	PET 50	130.0 ± 30.0	≥ 90	-	MLCC(적층세라믹콘덴서) 공정용
KDS	경박리	KDS-130A	PET 38	15.0 ± 5.0	97 ± 3	-	DAF 가공용

* Warranty :

All statements, technical information and recommendations about KOSTIC products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. We all KOSTIC products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

www.kostic.co.kr

Sales Team Tel : +81-31-984-2100, Sales Team FAX : +81-31-982-0458
R&D Team Tel : +81-31-949-0356, R&D Team Fax : +81-31-949-0549

KOSTIC KOREA CO., LTD