

# KOSTIC

## Release Paper Line Up

\* Release Force: TESA7475, 23℃ x 20hrs 전처리(70g/cm<sup>2</sup>가압)  
→ 4hrs 안정화, 180°Peel

PE/실리콘(S)	원지(PAPER)	두께(μm) Thickness	평량(g/m <sup>2</sup> )	이형 범위(gf/25mm) Release Force	특이사항
단면S	BG65(Blue Glassine)	52-57	63-67	경박(5-15)	무용제 실리콘
	WG65(White Glassine)	52-57	63-67	경박(5-15)	무용제 실리콘
	WG80(White Glassine)	65-70	78-82	경박(5-15)	무용제 실리콘

\* 관리 및 주의사항:작업 전 실리콘 처리면 확인, 운반/적재 시 주의(사용 잔여분 포장주의), 정전기, 먼지 주의, 작업 정체 시 이형물성 변화 확인  
\* 친환경/환경규제 대응: RoHS 및 할로젠프리 만족, 기타 규제 경우 분석 및 비사용보증서 대응(DoC)

\* Warranty :

All statements, technical information and recommendations about KOSTIC products are based upon tests believed to be reliable but do not constitute a guarantee or warranty.  
We all KOSTIC products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

[www.kostic.co.kr](http://www.kostic.co.kr)  
Sales Team Tel : +81-31-984-2100, Sales Team FAX : +81-31-982-0458  
R&D Team Tel : +81-31-949-0356, R&D Team Fax : +81-31-949-0549  
KOSTIC KOREA CO., LTD